

The following claims are presented for examination:

**Claim 1 (currently amended):** A tracking resistant resin composition comprising:

100 weight parts of at least one resin selected from the group consisting of

~~polyolefines~~, polyolefine resins and copolymers of different olefins;

Deleted: resins

~~0.1 to 1.5~~ 0.3 to 1.0 weight parts of a carbon black;

0.1 to 2 weight parts of a UV and light stabilizer; and

0.1 to 2 weight parts of an antioxidant[.]; wherein

the polyolefine resin is at least one of LDPE (low density polyethylene), MDPE (middle density polyethylene) and HDPE (high density polyethylene) which have a melt index of 0.1 to 1.0g/10min. and wherein

the carbon black has an average particle size of 60 nm or less, a surface area of 80 to 200 m<sup>2</sup>/g and a dibutyl acrylate adsorption of 100 to 200 cm<sup>3</sup>/100g.

**Claims 2-5 (canceled)**

**Claim 6 (currently amended):** The tracking resistant resin composition according to claim [5] 1, in which the carbon black has an average particle size of 30nm or less, a surface area of 100 to 170 m<sup>2</sup>/g and a dibutyl acrylate adsorption of 100 to 150 cm<sup>3</sup>/100g.

**Claim 7 (canceled)**

**Claim 8 (original):** The tracking resistant resin composition according to claim 1, in which the UV and light stabilizer is at least one selected from the group consisting of piperidines, benzophenones, and benzotriazoles.

Deleted: type compounds

Deleted: type compounds

Deleted: type compounds

Deleted: type

**Claim 9 (original):** The tracking resistant resin composition according to claim 8, in which the benzophenones, UV and light stabilizer is a compound of the 2,4-dihydroxy phenone structure which is substituted with a C<sub>1</sub>-C<sub>8</sub> alkyl group, a C<sub>6</sub>-C<sub>12</sub> cycloalkyl group or a C<sub>1</sub>-C<sub>8</sub> alkoxy group.

**Claim 10 (original):** The tracking resistant resin composition according to claim 8, in which the benzotriazoles, UV and light stabilizer is a compound of the 2-(2'-hydroxyphenyl)-benzotriazole structure which is substituted with a chlorine at 5 position and an alkyl group at 3' and 5' positions.

Deleted: type

**Claim 11 (original):** The tracking resistant resin composition according to claim 8, in which the piperidine is a 2,2,6,6-methyl piperidine.

Deleted: type compound

Deleted: type compound

**Claim 12 (original):** The tracking resistant resin composition according to claim 11, in which the 2,2,6,6-methyl piperidine is at least one selected from the group consisting of 2,2,6,6-pentamethyl-4-piperidinyl, N-butyl-2,2,6,6-tetramethyl-4-piperidine amine, hexanediyl(2,2,6,6-tetramethyl-4-piperidinyl)imino and 4-hydroxy-2,2,6,6-tetramethyl-1-piperidine.

Deleted: type compound

**Claim 13 (original):** The tracking resistant resin composition according to claim 8, in which the UV and light stabilizer is any one of methyl piperidine and benzophenone or a mixture thereof.

Deleted: a

Deleted: type compound

Deleted: a

Deleted: type compound

**Claim 14 (original):** The tracking resistant resin composition according to claim 8, in which the UV and light stabilizer is any one of 2,2,6,6-methyl piperidine and 2-(2'-hydroxy phenyl)-benzotriazoles or a mixture thereof.

Deleted: a

Deleted: type compound

Deleted: a

Deleted: type compound

**Claim 15 (original):** The tracking resistant resin composition according to claim 8, in which the UV and light stabilizer is at least one of N-C<sub>1</sub>-C<sub>8</sub> alkyl-substituted derivatives of a 2,2,6,6-tetramethyl-1-piperidine.

Deleted: compound

**Claim 16 (original):** The tracking resistant resin composition according to claim 1, in which the UV and light stabilizer is 0.3 to 1 weight parts relative to 100 weight parts of the resin.

**Claim 17 (original):** The tracking resistant resin composition according to claim 1, in which the antioxidant is at least one selected from the group consisting of hindered phenol antioxidants, phosphite antioxidants and sulfur-containing antioxidants.

Deleted: type

Deleted: type

**Claim 18 (original):** The tracking resistant resin composition according to claim 17, in which the hindered phenol antioxidant is at least one selected from the group consisting of tetrakis(3-(3,5-di-tert-butyl-4-hydroxy phenyl)propionate), thiodiethylenbis(3-(3,5-di-tert-butyl-4-hydroxy phenyl)propionate and 6,6'-di-tert-butyl-2,2'-thiodi-p-cresol.

Deleted: type

**Claim 19 (original):** The tracking resistant resin composition according to claim 17, in which the phosphite antioxidant is any one of tris(2,4-di-tert-butyl phenyl)phosphite and di-tert-butyl phenyl phosphonite or a mixture thereof.

Deleted: type

**Claim 20 (original):** The tracking resistant resin composition according to claim 17, in which the sulfur-containing antioxidant is any one of dilauryl thiopropionate and dimyristyl thiodipropionate or a mixture thereof.

**Claim 21 (original):** The tracking resistant resin composition according to claim 1, in which the antioxidant is 0.2 to 1 weight parts relative to 100 weight parts of the resin.

**Claims 22-23 (canceled)**